



Products in needled white glass wool felt

These product types are made from binder-free, white fibreglass felts. Their high density is assured by an effective mechanical needling system while glass filaments assure high thermal performance. Depending on specific requirements, they can be coated on one or both sides with smooth aluminium or aluminium mesh, white or black glass cloth, glass veil and other materials on request.

Products made from needled felt are flexible, compact and have a very low level of dust emission; these features made them easier and more comfortable to handle. They guarantee constant performance over time thanks to their totally inorganic origin. They are especially made to withstand considerable temperature changes.

They can be supplied with densities ranging from 60 to 180 kg/m³, depending on thickness and design, in order to obtain a product with correct resistance to handling. Thicknesses can vary from 6 to 40 mm.

They are mainly used as heat insulation in the production of domestic and industrial ovens, as lagging for cisterns and tanks, as heat and sound insulation for exhaust pipes, and for other industrial purposes

TECHNICAL PROPERTIES

Feature	Value	Unit of measurement	Standard		
Reaction to fire	Euroclass A1	-	EN 13501		
Melting temperature	900 °C	°C	DIN 4102/T17		
Working temperature	between 500 and 600 °C	°C	EN 14706		
Water vapour diffusion resistance (μ)	1.4	-	EN 12086		
Thermal conductivity (λ) at an average temperature of:	Density				
	60kg/m ³	80kg/m ³	100kg/m ³	130kg/m ³	180kg/m ³
150 °C	0.050 W/m·K	0.047 W/m·K	0.043 W/m·K		
200 °C	0.059 W/m·K	0.055 W/m·K	0.055 W/m·K	0.062 W/m·K	0.043W/m·K
250 °C	0.070 W/m·K	0.064 W/m·K	0.063 W/m·K		
300 °C				0.076 W/m·K	0.057 W/m·K
400 °C				0.087 W/m·K	0.074 W/m·K

PHYSICAL AND CHEMICAL PROPERTIES

- Appearance: white material in a solid aggregate state.
- Specific temperature at which the physical state changes: softening point: littleton softening point (viscosity) 107.6 poises, approximately 850°C
- Hazardous products of decomposition: none
- Flashpoint: irrelevant
- Flammability: irrelevant

PACKAGING

The products, die-cut or shaped according to customer specifications, can be packed in polythene bags or in cardboard boxes.